


Isophorone Diisocyanate (IPDI)

Description and synonyms

- Monomeric cycloaliphatic diisocyanate or 3-isocyanatomethyl-3,5,5-trimethylcyclohexylisocyanate
- CAS number: 4098-71-9

Chemical Structure

- $C_{12}H_{18}N_2O_2$ or



Molecular Weight

$M_r = 222.28$

Specifications

(valid for the product manufactured in Pont-de-Claix, France)

Colour	≤ 30 HAZEN (APHA)
Hydrolysable chlorine	< 200 ppm
Total chlorine	< 400 ppm
Assay	> 99.5 % by wt
NCO content	37.5 to 37.8% by weight

The analytical methods are available upon request

Physical Properties

Appearance	Clear liquid
Odour	Pungent
Bulk density	1058 kg/m ³
Specific heat at 20°C	1.68 kJ/kg
Temperature of crystallization	< - 60°C
Boiling point under 1.33 KPa	158°C
Boiling point under 1013 hPa	310°C (decomposes)
Vapour pressure: at 20°C	0.04 Pa
Vapour pressure: at 50°C	0.9 Pa
Self-ignition temperature	430°C

Isophorone Diisocyanate (IPDI)

Flash point (closed cup)	155°C
Vapour density (air = 1)	7.63
Concentration of saturated vapour at 20°C	<1 mbar
Concentration of saturated vapour at 100°C	1.7 mbar
Refractive index nD 25	1.483
Dynamic viscosity at 20°C	15 mPa.s

Applications

- IPDI is used in the chemical synthesis of aliphatic polyisocyanates and polyurethanes, such as aqueous dispersible polyurethane polymers (PUD) showing exceptional weathering resistance.

Hazardous properties and safety instructions

- Monomeric diisocyanates are reactive chemicals that must only be handled under very strictly controlled conditions. They are strongly irritating to the skin, eyes and the respiratory tract and act as skin and respiratory tract/lung sensitizers.
- Before handling this product it is therefore very important to carefully read its safety data sheet.

Packaging and transport

Packaging (please contact our sales team for more details)

- Deliveries of 860 kg net weight pallets (4 drums of 215 kg net weight).
- Other packaging: upon request

Transport

- Regulated. For more precise details, please consult the safety data sheet

Isophorone Diisocyanate (IPDI)

Storage conditions and shelf-life

- IPDI is sensitive to moisture and should be kept in its original container or in a volume tank under dry nitrogen blanketing, for example.
- Appropriate storage for 12 months does not normally affect the product in any way if it is stored in its sealed original drums in proper storage conditions at temperatures below 40°C.

warning to users

The information contained in this document is given in good faith and based on our current knowledge. It is only an indication and is in no way binding, particularly as regards infringement of or prejudice to third parties through the use of our products. VENCOREX guarantees that its products comply with its sales specifications. This information must on no account be used as a substitute for necessary prior tests which alone can ensure that a product is suitable for a given use. Users are responsible for ensuring compliance with local regulation and for obtaining the necessary certifications and authorizations. Users are requested to check that they are in possession of the latest version of the present document and VENCOREX is at their disposal to supply any additional information.