

Product Chemical name Peroxide content, physical form	CAS N.	Standard packaging	Recommended storage temperature (°C)	UN-n°	Applications and properties
RETIC A 150 2,2'-[(4-methylphenyl) imino]bisethanol 98%, liquid	3077-12-1	Kg 30 Container	max +30	In combination with Dibenzoyl peroxide one obtains a relatively short gel and curing time of unsaturated polyester resins; high activity. Non toxic.
RETIC A 15 2,2'-[(4-methylphenyl)imino]bisethanol 10% in 1-isopropyl-2,2-dimethyltrimethylene diisobutyrate, liquid	3077-12-1	Kg 30 Container	max +30	In combination with Dibenzoyl peroxide one obtains a relatively short gel and curing time of unsaturated polyester resins; high activity. Non toxic.
RETIC A 100 N,N-Dimethyl-p-toluidine 98%, liquid	99-97-8	Kg 30 Container	max +30	2810	In combination with Dibenzoyl peroxide one obtains a relatively short gel and curing time of unsaturated polyester resins; high activity.
RETIC A 200 N,N-Dimethylaniline 98%, liquid	121-69-7	Kg 30 Container	max +30	2253	In combination with Dibenzoyl peroxide one obtains a relatively short gel and curing time of unsaturated polyester resins; high activity.
RETIC A 300 N,N-Diethylaniline 98%, liquid	91-66-7	Kg 30 Container	max +30	2432	In combination with Dibenzoyl peroxide one obtains a relatively short gel and curing time of unsaturated polyester resins; high activity.
RETIC C 60 X Cobalt octoate 6% in xylene, liquid	68409-81-4	Kg 30 Container	5....30	1993	In combination with Ketone peroxides short gel and curing time (depending on the dosage); the storage time is almost unlimited. Non toxic.
RETIC SLOW BK 100 4-tert-butylpyrocatechol 98% , liquid	98-29-3	Kg 30 Container	max +30	3265	To increase pot life and gel time; also curing time is also slightly delayed.
RETIC SLOW BK 10 X 4-tert-butylpyrocatechol 15% in 1-isopropyl- 2,2-dimethyltrimethylene diisobutyrate, liquido	98-29-3	Kg 30 Container	max +30	3265	To increase pot life and gel time; also curing time is also slightly delayed.
RETIC SLOW CH 10 P-benzoquinone 15% in styrene e butanone, liquid	106-51-4	Kg 30 Container	10....20	1993	To increase pot life of SMC and BMC.
RETIC SLOW PK 100 2,6-di-tert-butyl-p-cresol, liquid	128-37-0	Kg 30 Container	max +30	3077	To increase pot life of SMC and BMC.