

Product Chemical name Peroxide content, physical form	Peroxide CAS N.	Standard packaging	Active Oxygen cont. (%)	Recommended storage temperature (°C)	SADT (°C)	UN-n°	Applications and properties
RETIC BP W 25 Di-benzoyl Peroxide 75% in water, powder	94-36-0	kg 25 Cardboard box	5,0	5....30	50	3104	Hot curing of unsaturated polyester resins.
RETIC BP 50 WHITE Di-benzoyl Peroxide 50% in inert filler, white paste	94-36-0	kg 25 Plastic box / tubes and tins	3,30	5....30	50	3108	Hot curing of unsaturated polyester resins.
RETIC BP 50 RED Di-benzoyl Peroxide 50% in inert filler, red paste	94-36-0	kg 25 Plastic box / tubes and tins	3,30	5....30	50	3108	Hot curing of unsaturated polyester resins.
RETIC BP 50 BLU Di-benzoyl Peroxide 50% in inert filler, blu paste	94-36-0	kg 25 Plastic box / tubes and tins	3,30	5....30	50	3108	Hot curing of unsaturated polyester resins.
RETIC BP 50 LA Di- benzoyl Peroxide 50% in phlegmatizer, pasty	94-36-0	kg 25 Plastic box	3,30	5....30	50	3108	Hot curing of unsaturated polyester resins. Easy dispersion due to its low viscosity.
RETIC BP 40 LV Di- benzoyl Peroxide 40% in 2-hethylhexyl benzoate, suspension	94-36-0	kg 20 Plastic box	2,64	5....25	60	3107	Hot curing of unsaturated polyester resins and acrylates. Easy dispersion and easy process.
RETIC BP 50 PW Di-benzoyl Peroxide 50% in Dicyclohexyl Phtalate, powder	94-36-0	kg 20 Cardboard box / pre- dosed bags	3,30	5....30	60	3106	Hot curing of unsaturated polyester resins and acrylates. Easy dispersion and easy process.
RETIC BP 30 Q PW Di-benzoyl Peroxide 30% in quartz, powder	94-36-0	kg 20 Cardboard box / pre- dosed bags	1,98	5....30	50	3077	Hot curing of unsaturated polyester resins and acrylates. Easy dispersion and easy process.
RETIC BP 20 Q PW Di-benzoyl Peroxide 20% in quartz, powder	94-36-0	kg 20 Cardboard box / pre- dosed bags	1,32	5....30	50	3077	Hot curing of unsaturated polyester resins and acrylates. Easy dispersion and easy process.

Product Chemical name Peroxide content, physical form	Peroxide CAS N.	Standard packaging	Active Oxygen cont. (%)	Recommended storage temperature (°C)	SADT (°C)	UN-n°	Applications and properties
RETIC BP 30 PW Di-benzoyl Peroxide 30% in inert filler, powder	94-36-0	kg 20 Cardboard box / pre- dosed bags	1,98	5....30	60	3077	Hot curing of unsaturated polyester resins and acrylates. Easy dispersion and easy process.
RETIC BP 15 G Di-benzoyl Peroxide 15% in inert filler, grey paste	94-36-0	kg 25 / 200 Plastic box	0,92	5....30	50	3077	Hot curing of unsaturated polyester resins. Used for chemical anchors.
RETIC BP 15 Q/N Di-benzoyl Peroxide 15% in inert filler, black paste	94-36-0	kg 25 / 200 Plastic box	0,92	5....30	50	3077	Hot curing of unsaturated polyester resins. Used for chemical anchors.
RETIC BP 13 QB Di-benzoyl Peroxide 13% in quartz and inert filler, white paste	94-36-0	kg 25 / 200 Plastic box	0,86	5....30	50	3077	Hot curing of unsaturated polyester resins. Used for chemical anchors.
RETIC BP 17 QN Di-benzoyl Peroxide 17% in quartz and inert filler, black paste	94-36-0	kg 25 / 200 Plastic box	1,12	5....30	50	3108	Hot curing of unsaturated polyester resins. Used for chemical anchors.