

Product Chemical name Peroxide content, physical form	Peroxide CAS N.	Standard packaging	Active Oxygen cont. (%)	Recommended storage temperature (°C)	SADT (°C)	UN-n°	Applications and properties
RETIC TBH 70 Tert-butyl hydroperoxide 70% in water, liquid	75-91-2	Kg 25 Container	12,44	5...30	80	3109	Polymerization of Alkyd/Styrene mixtures.
RETIC TBH 13 Tert-butyl hydroperoxide 13% in water, liquid	75-91-2	Kg 25 Container	2,25	5...30	80	3109	Polymerization of Alkyd/Styrene mixtures. Less active than TBH 70.
RETIC PO Tert-butyl 2-Ethylperoxyhexanoate 99%, liquid	3006-82-4	Kg 20 Container	....	max 15	35	3113	Polymerization initiator for high density polyethylene, Polystyrene, PMMA.
RETIC PIN Tert-butyl 3,5,5-trimethylperoxyhexanoate 99%, liquid	13122-18-4	Kg 20 Container	6,80	max 30	60	3105	Polymerization initiator for high density polyethylene, Polystyrene, PMMA.
RETIC PIN S1 Tert-butyl 3,5,5-trimethylperoxyhexanoate 90% in 2,4 pentanedione , liquid	13122-18-4	Kg 20 Container	6,25	max 30	55	3105	Polymerization initiator for high density polyethylene, Polystyrene, PMMA. Less active than PIN.
RETIC PB Tert-butyl perbenzoate 99%, liquid	614-45-9	Kg 25 Container	8,16	10...30	60	3103	Polymerization initiator for high density polyethylene, Polystyrene, PMMA.
RETIC BCC Bis(4-tert-butylcyclohexyl)peroxidicarbonate 99%, powder	15520-11-3	kg 20 Cardboard box	3,70	max 15	40	3114	Polymerization initiator for PVC, Polystyrene, PMMA.
RETIC BP W 25 Di-benzoyl Peroxide 75% in water, powder	94-36-0	kg 25 Cardboard box	5,0	5...30	50	3104	Polymerization of styrene.

Product Chemical name Peroxide content, physical form	Peroxide CAS N.	Standard packaging	Active Oxygen cont. (%)	Recommended storage temperature (°C)	SADT (°C)	UN-n°	Applications and properties
RETIC BEC OO-tert-butyl O-(2-ethylhexyl) peroxycarbonate 99%, liquid	34443-12-4	Kg 20 Container	6,30	max 30	60	3105	Polymerization initiator for high density polyethylene, Polystyrene, PMMA.
RETIC BIC O,O-tert-butyl isopropyl monoperoxycarbonate 75%, liquid	2372-21-6	Kg 20 Container	6,80	max 25	60	3103	Polymerization initiator for high density polyethylene, Polystyrene, PMMA.
RETIC DB Di-tert-butyl peroxide 98%, liquid	110-05-4	Kg 25 Container	10,70	max 30	80	3107	Polymerization initiator for PE, PP, PS and PMMA.
RETIC AZDN 2,2'-dimethyl-2,2'-azodipropionitrile 98%, powder	78-67-1	kg 25 Cardboard box	....	max 25	50	3234	Polymerization initiator for PVC, PS and PMMA.
RETIC LP Dilauroyl peroxide 99%, powder	105-74-8	kg 20 Cardboard box	4,0	max 30	50	3106	Curing of acrylic resins.
RETIC LP M Dilauroyl peroxide 99%, micronized product	105-74-8	kg 20 Cardboard box	4,0	max 30	50	3106	Curing of acrylic resins. Easy dispersion with fine powder.